





Effective March 2018

HQR

| DESCRIPTION | | | |
|--|-------------------|-----------------------------------|---|
| Total thickness | EN 428 | mm | 3.10 |
| Thickness of the wearlayer | EN 429 | mm | 0.50 |
| Weight | EN 430 | g / m ² | 2200 |
| Width of sheet | EN 426 | m | 4 |
| Length of sheet | EN 426 | lm | 25 |
| CLASSIFICATION | | | |
| Norm / Product specification | - | - | EN 653 |
| European classification | EN 685 | class | 33-42 |
| Fire rating | AS ISO 9239-1 | kW / m ² | 8 |
| | | smoke% / min | 107 |
| Slip resistance | AS 4586 | class | R10 |
| | AS 4586:2013 | class | P2 |
| PERFORMANCES | | | |
| Wear group | EN 660/1 | - | T |
| Dimensional stability | EN 434 | % | 0.05 |
| Residual indentation | EN 433 | mm | 0.18 |
| Colour fastness | EN 20 105 - B02 | degree | ≥ 6 |
| Impact sound insulation | EN ISO 717-2 | dB | 16 |
| Acoustic rating | AS ISO 717.2-2004 | L _{n,w} + C _i | 61 |
| Surface treatment | - | - | Pureclean |
| VOC | ASTM D5116 | mg/m ³ /hr (24hrs) | Pass |
| Guarantee Residential | - | years | 15 |
| Guarantee Commercial | - | years | 10 |
|  | EN 14041 | |    |