





DESCRIPTION			
Total thickness	EN ISO 24346 (EN 428)	mm	3.35
Wearlayer thickness	EN ISO 24340 (EN 429)	mm	0.65
Weight	EN ISO 23997 (EN 430)	g/sq.m	2825
Width of sheet	EN ISO 24341 (EN 426)	cm	200
Length of sheet	EN ISO 24341 (EN 426)	lm	25
CLASSIFICATION			
Norm / Product specification	-	-	EN 651
European classification	EN ISO 10874 (EN 685)	class	34 - 42
Fire rating	AS ISO 9239- 1	kW/ m2	7.9
		smoke %/ min	183
Static electrical propensity	EN 1815	kV	< 2
Slip resistance	AS 4586:2013	class / appendix A	R10
		class / appendix D	P2
PERFORMANCE			
Wear resistance	EN 660.2	mm <sup>3</sup>	≤ 2.00
Wear group	NF189	group	T
Dimensional stability	EN ISO 23999 (EN 434)	%	≤ 0.40
Residual indentation (requirement)	EN ISO 24343-1 (EN 433)	mm	≤ 0.20
Residual indentation (average value measured)	-	mm	≈ 0.08
Impact sound insulation	EN ISO 717-2	dB	19
Transfer noise	AS/ISO 717.2	Ln,w (C1)	59 (-1)
Castor chair test (type W)	ISO 4918 (EN 425)	-	OK
Thermal conductivity	EN ISO 10456 (EN 12 524)	W/(m.K)	0.25
Colour fastness	EN 20 105 - B02	degree	≥ 6
Surface treatment	-	-	Protecsol® 2
Chemical products resistance	EN ISO 26987 (EN 423)	-	OK
Anti-bacterial activity (E. coli - S. aureus - MRSA) (2)	ISO 22196	-	> 99 % Inhibits growth
ENVIRONMENT / INDOOR AIR QUALITY			
VOC	ASTM D5116		0.03mg/m2/hr (24 hours)
Certification	-	-	Floorscore®, Green Tag
CE MARKING			
	EN 14041	-	
		-	
 <p><b>Effective 09/2017</b></p>			