

**DESCRIPTION**

Total thickness	EN 428	mm	3.00
Thickness of wearlayer	EN429	mm	0.65
Weight	EN 430	g/m <sup>2</sup>	2300
Width of sheet	EN 426	cm	200
Length of sheet	EN 426	lm	25





**CLASSIFICATION**

Norm / Product specification	-	-	EN 651
European classification	EN 685	class	34 - 42
Fire rating / Critical flux	EN ISO 9239-1	kW/m <sup>2</sup>	8.37
Fire rating / Smoke density	EN ISO 9239-1	% min	225
Static electrical propensity	EN 1815	kV	< 2
Slip resistance wet: Ramp test oil	DIN 51130	class	R10

**PERFORMANCE**

Wear resistance	EN 660.2	mm <sup>3</sup>	≤ 2.0
Wear Group	EN 651	group	T
Dimensional stability	EN 434	%	≤ 0.40
Residual indentation (exigency)	EN 433	mm	≤ 0.20
Residual indentation (measure)	-	mm	0.11
Impact sound insulation	EN ISO 717-2	dB	17
Castor chair test (type W)	EN 425	-	OK
Thermal conductivity	EN 12 524	W/(m.K)	0.25
Colour fastness	EN 20 105 - B02	degree	≥ 6
Chemical products resistance	EN 423	class	ok
Anti-bacterial and fungicidal treatment	-	-	Sanosol®
Surface treatment	-	-	Protecsol®
TVOC after 28 days	ISO 16000-6	µg/ m <sup>3</sup>	< 100

**CE MARKING**

	EN 14041	-	  
		-	