


Effective August 2017

**ESSENCE**

<b>DESCRIPTION</b>			
Total thickness	EN 428	mm	2.90
Thickness of the wearlayer	EN 429	mm	0.30
Weight	EN 430	g / m <sup>2</sup>	2000
Width of sheet	EN 426	m	4
Length of sheet	EN 426	lm	25
<b>CLASSIFICATION</b>			
Norm / Product specification	-	-	EN 653
European classification	EN 685	class	33-42
Fire rating	AS ISO 9239-1	kW / m <sup>2</sup>	8.92
		smoke% / min	177
Slip resistance	AS 4586	class	R10
	AS 4586:2013	class	P2
<b>PERFORMANCES</b>			
Wear group	EN 660/1	-	T
Dimensional stability	EN 434	%	0.05
Residual indentation	EN 433	mm	0.20
Colour fastness	EN 20 105 - B02	degree	≥ 6
Impact sound insulation	EN ISO 717-2	dB	16
Surface treatment	-	-	Pureclean
VOC	ASTM D5116	mg/m <sup>3</sup> /hr (24hrs)	0.01
Guarantee Residential	-	years	15
Guarantee Commercial	-	years	10
	EN 14041		