






|   | PRODUCT CHARACTERISTICS          |             |                   |  |
|---|----------------------------------|-------------|-------------------|--|
|   | Standard                         | Requirement | Unit              | Results  |
|   | <b>PRODUCT DESCRIPTION</b>       |             |                   |  |
| Surface treatment   | -                                | -           | -                 | PUR PROTECT  |
| Surface complex   | -                                | -           | -                 | 100% PVC   |
| Foam  | -                                | -           | -                 |  |
| Thickness   | EN ISO 24346                     | -           | mm                | <b>6 mm</b>       |
| Weight  | EN ISO 23997                     | -           | kg/m <sup>2</sup> | 3.7  |
| Length  | EN ISO 24341                     | -           | lm                | 20.5 Standard  |
| Width   | EN ISO 24341                     | -           | lm                | 1.5  |
|   | <b>SPORT PROPERTIES</b>          |             |                   |  |
| Shock absorption  | EN 14808                         | ≥ 25        | %                 | <br>P1            |
| Vertical deformation  | EN 14809                         | ≤ 3.5       | mm                | ≤ 3.5  |
| Sliding coefficient   | EN 13036-4                       | 80 to 110   | -                 | 80 - 110   |
| Ball bounce   | EN 12235                         | ≥ 90        | %                 | ≥ 90   |
| Ball speed  | UEFA                             | 50 to 65    | cm                | 55   |
|   | <b>TECHNICAL CHARACTERISTICS</b> |             |                   |  |
| Abrasion resistance   | EN ISO 5470-1                    | ≤ 1000      | mg                | ≤ 350  |
| Impact resistance   | EN 1517                          | ≥ 8         | N/m               | ≥ 8  |
| Indentation resistance  | EN 1516                          | ≤ 0.5       | mm                | ≤ 0.5  |
| Impact sound insulation   | EN ISO 717-2                     | -           | dB                | 18   |
|   | <b>CLASSIFICATION</b>            |             |                   |  |
| Feu   | EN 13501-1                       | -           | -                 |                 |
| Treatment   | -                                | -           | -                 |                 |
|  | DOP-005-1007-A                   | -           | -                 | Fire<br>Shock Absorption<br>Sliding Coefficient<br>Abrasion Resistance<br>Resistance to rolling load |