

DESCRIPTION

Total thickness	EN 428	mm	6.00
Thickness of wearlayer	EN 429	mm	2
Weight	EN 430	g/m ²	9380
Tile size	EN 427	mm	635 x 635





CLASSIFICATION

Norm / Product specification	-	-	EN 649
European classification	EN 685	class	34 - 43
K rating	-	class	
Fire rating / Critical flux	EN ISO 9239-1	kW/m ²	
Fire rating / Smoke density	EN ISO 9239-1	% min	
Static electrical propensity	EN 1815	kV	< 2
Slip resistance wet : Pendulum	AS/NZ 4586 appendix a	-	
Slip dry resistance : Coefficient of friction	AS/NZ 4586 appendix b	-	
Slip resistance wet : ramp test	AS/NZ 4586 appendix c	-	
Slip resistance wet: ramp test with oil	AS/NZ 4586 appendix d	-	

PERFORMANCE

Wear resistance	EN 660.2	mm ³	≤ 2
Wear group	EN 649	-	T
Type Binder content	ISO 10582	type	I
Dimensional stability	EN 434	%	≤ 0.25
Shore hardness	EN ISO 868	H _D	≥ 55
Castor chair test (type W)	EN 425	-	OK
Thermal conductivity	EN 12524	W/(m.K)	0.25
Colour fastness	EN 20 105 - B02	degree	≥ 6
Chemical products resistance	EN 423	-	OK
Surface treatment	-	-	PUR+
TVOC after 28 days	ISO 16000-6	µg/ m ³	< 100

CE MARKING

	EN 14041	-	  
		-	