











DESCRIPTION			
Type of flooring	EN ISO 24011 (EN 548)	-	Linoleum with LPX surface treatment
Pattern	-	-	Scattered metallic design
Total thickness	EN ISO 24346 (EN 428)	mm	2.5
Backing	-	-	Jute fabric
Weight	EN ISO 23997 (EN 430)	g/sqm	2900
Width of sheet	EN ISO 24341 (EN 426)	cm	200
Length of sheet	EN ISO 24341 (EN 426)	m	20 - 31
CLASSIFICATION			
Norm / Product specification	-	-	EN ISO 24011
European classification	EN ISO 10874 (EN 685)	class	23 / 34 / 42 / 43
Fire rating	EN 13501-1	class	Cfl-s1*
Slip resistance	ASR A1.5 /DIN 51130 – BGR 181	class	R9
Dynamic friction coefficient	EN 13893	-	DS (>0.30)
Impact sound insulation	EN ISO 10140	dB	5 dB
PERFORMANCES			
Residual indentation	EN ISO 24343-1 (EN 433)	mm	≤ 0.15
Colour fastness	EN ISO 105 - B02	degree	≥6
Point contact resistance	VDE 0100	kOhm	>200
Static electrical propensity	EN 1815	kV	app. 2.0
Castor chair test (Type W)	ISO 4918	-	OK
Thermal resistance	EN 12667	Sqm,K/W	0.015
Thermal conductivity	EN ISO 10456 (EN 12 524)	W/(m.K)	0.17
Surface treatment	-	-	LPX
Chemical products resistance	EN ISO 26987 (EN 423)	class	Resistance to fat and mineral oil and short term resistance against diluted acids
Antibacterial activity	JIS Z 2801	-	DLW linoleum has an antibacterial activity
CERTIFICATES AND LABELS			
    			
CE MARKING			
	EN 14041 : 2004 AC : 2006	-	  
		-	

\* Glued according to certificate.  
DOP numbers available from your local branch.



Depending on light exposure, the product colour can vary, due to linoleum natural oxidization process. The process is reversible.  
We recommend that the samples be exposed to sunlight for several hours prior to making a final color choice