

DESCRIPTION

Total thickness on grainside	EN 428	mm	2.20
Weight	EN 430	g/m ²	2200
Width of sheet	EN 426	cm	200
Length of sheet	EN 426	lm	20





CLASSIFICATION

Norm / Product specification	-	-	EN 649
European classification	EN 685	class	34 - 43
Fire rating	EN 13501-1	class	C _{fl} -s1
Slip resistance wet : ramp test	DIN 51 097	class	A B

PERFORMANCE

Wear resistance	EN 660.2	mm ³	≤ 2.0
Wear group	EN 649	-	T
Dimensional stability	EN 434	%	≤ 0.40
Residual indentation	EN 433	mm	≤ 0.10
Thermal conductivity	EN 12524	W/(m.K)	0.25
Colour fastness	EN 20 105 - B02	degree	≥ 6
Chemical products resistance	EN 423	-	OK
Anti-bacterial and fungicidal treatment	-	-	Sanosol®

CE MARKING

	EN 14041	-	  
		-	